



Technical Report: 96250480261
Date Received: FEBRUARY 17, 2025

FEBRUARY 20, 2025
Page 1 of 4

CONG TY TNHH THUONG MAI DICH VU THAI DANH
SO 210, AN PHU DONG 3, TO 38, KP5, PHUONG AN PHU DONG, QUAN 12, TP HCM, VIET NAM

Sample Description:	FIBER	Sample Size:	/
Vendor:	CONG TY TNHH THUONG MAI DICH VU THAI DANH		
Manufacturer:	/	VPN:	/
Buyer:	/	SKN/SKU No.:	/
Agent:	/		/
Labeled Age Grade:	/	PO No.:	/
Appropriate Age Grade:	/	Ref #:	/
Client Specified Age Grade:	/	Country of Origin:	/
Tested Age Grade:	/	Assortment No.:	/
UPC Code:	/	Department No.:	/
Phase of Production:	/	Item#:	/
Color:	/	Date of Production:	/
Program:	/	Model/Style#:	/
Previous No:	N/A	Country of Destination:	/

TEST PROPERTY	PASS	FAIL	DATA	N/A	Remark
CA TB 117-2013-section 3- Flammability of resilient filling material test	X				



CONG TY TNHH THUONG MAI DICH VU THAI DANH
Technical Report: **96250480261**
FEBRUARY 20, 2025
Page 2 of 4

If there is any question regarding this report, please contact the following lab personnel:

Administrative inquiries, please contact:

Primary Contact: Elise Vo, Tel: 84-028-37421-604 ~ 6, Ext: 394; email: elise.vo@bureauveritas.com
Back-up Contact: Cynthia Vuong, Tel: 848-37421-604 ~ 6, Ext: 641; email: cynthia.vuong@bureauveritas.com

Technical inquiries, please contact:

Primary Contact: Terry Nguyen, Tel: 84-028-37421-604 ~ 6, Ext: 355; email: terry.nguyen@bureauveritas.com
Back-up Contact: Louis Tran, Tel: 84-028-37421-604 ~ 6, Ext: 339; email: louis.tran@bureauveritas.com

BUREAU VERITAS CONSUMER PRODUCTS SERVICES (VN) LTD.

TERRY NGUYEN
LAB MANAGER – HARDLINE, TOYS & JUVENILE PRODUCTS DIVISION



RESULT(S):

Flammability of resilient filling material test

Test Method : California Technical Bulletin CA TB 117-2013 section 3

Tested Item(s) : FIBER

RESULT FOR INITIAL TEST:

SPECIMEN	TRANSITION TO OPEN FLAMING	SMOLDERING	CHAR LENGTH (IN)
1	N	N	0.6
2	N	N	0.6
3	N	N	0.7

RESULT FOR ADDITIONAL TEST: N/A

SPECIMEN	TRANSITION TO OPEN FLAMING	SMOLDERING	CHAR LENGTH (IN)
1	/	/	/
2	/	/	/
3	/	/	/
OVERALL RATING:	PASS		

Note / Key:

Y=Yes

DATA = Record data
only

N=No

NA = Not Applicable

P=Pass

NR= Not requested

F=Fail

NT=Not Tested

PASS/FAIL CRITERIA

A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:

- The mock-up test specimen continues to smolder after the 45 minute test duration;
- A vertical char length (measured as described in step 17.9 of ASTM E1353-08a^{e1}) of more than 1.5 inches (38 mm) develops on the cover fabric.
- The mock-up test specimen transitions to open flaming.

2. The resilient filling material passes the test if three mock-up specimens pass the test.

3. If more than one specimen fails, the resilient filling material fails the test.

4. If any one of the three initial specimens fails, repeat the test on additional three specimens.

5. If all three additional specimens pass the test, the resilient filling material passes the test. If any one of the additional three specimens fails, the resilient filling material fails the test.

